




CO₂e RANKING



237 HDPE MONOMATERIAL

263 HDPE 6 LAYER

435 TINPLATE

488 PET MONOMATERIAL

526 GLASS

1.353 ALUMINIUM

g CO₂ equivalents per 1 litre bottle

Consideration framework is cradle-to-grave (without recycling; with incineration, as small packaging is usually incinerated when filled with hazardous substances)

